



# Specification

## AG411-1 Pink

Edition: YZ2019-01TDS

Assays			Values	Method
Content	CAS-NO.	CI-NO.		
Mica	12001-26-2	77019	68~78 wt%	YUNZHU
TiO <sub>2</sub>	13463-67-7	77891	21~30 wt%	YUNZHU
Pigment red 22	6448-95-9	12315	0~3 wt%	YUNZHU

### Visual evaluation

Color		pass	YUNZHU
Luster		pass	YUNZHU
Density		2.4~3.1 g/cm <sup>3</sup>	ISO 787-10
Bulk density		16~22 g/100ml	DIN 53466
Particle size	80 % within the range 10~60μm	pass	Laser diffraction
PH – value	10 % aqueous slurry	5~9	ISO 787-9
Loss on drying	105 °C	≤0.5 wt %	ISO 787-2
Oil absorption		50 ~ 90 g oil/100g powder	ISO 787-5
Conductance		≤100 μs/cm	ISO 787-14

### Heavy metals

Pb	≤	30	ppm	YUNZHU
As	≤	5	ppm	YUNZHU
Hg	≤	1	ppm	YUNZHU
Cd	≤	5	ppm	YUNZHU

## Shanghai Yunzhu Pigment Technology Co.,Ltd.

No.27 Lane 111,Shunda Road,Nanxiang Town, Jiading Area,Shanghai,China.

Tel: 0086-21-56377935 / 56373532

Fax: 0086-21-66102842

Home Page: [www.chinayunzhu.com](http://www.chinayunzhu.com)

E-mail: [shyz@chinayunzhu.com](mailto:shyz@chinayunzhu.com)